Technical Data Sheet



RECOVYN™ PVC 550GA

Pioneering circular PVC, produced using 100 % recycled carbon feedstock from plastic waste

TYPE

Copolymer of vinyl chloride and vinyl acetate produced by suspension polymerisation.

TYPICAL PROPERTIES

| Property | Reference standard | Unit | Typical value* |
|------------------------------------|-----------------------|--------|----------------|
| K-value | ISO 1628-2 | - | 50 |
| Vinyl acetate content | Internal | % | 13 |
| Apparent bulk density ¹ | ISO 60 | kg/dm³ | 0.530 |
| Retained on 180 µm | ISO 1624 | % | ≤ 1.5 |
| Retained on 63 µm | ISO 1624 | % | ≥ 40 |
| Volatiles content | ISO 1269 | % | ≤ 0.3 |

¹with antistatic agent addition

PROCESSING TECHNIQUES

After mixing with appropriate additives, RECOVYN™ PVC 550GA is suitable for processing by a number of techniques including calendering, extrusion and solution.

APPLICATIONS

RECOVYNTM PVC 550GA is recommended for applications where high fluidity, fast gelation or easy dissolution are required, typically:

- · vinyl records
- highly-filled calendered floorings
- insulation foams
- · solvent based glues and adhesives.

Some applications of this product may be regulated or restricted by applicable laws and regulations or by national or international standards, which may among other concern medical devices, pharmaceutical industry, cosmetics packaging, personal care packaging, food, food additives, feed packaging, drinking water, water treatment, etc. The buyer and the eventual user, in his sole and entire liability, shall respect those standards, orders of any relevant authority, and all existing patents and intellectual properties rights; and shall comply with the laws, regulations, standards and/or recommendations applicable to our products and/or to his activity, to their final articles and/or their use. The buyer and the eventual user must independently determine the suitability of this product for any particular purpose and its manner of use.



| TDS RECOVYN™ PVC 560GA | | | | | |
|------------------------|------------|-------|----|--|--|
| Date | April 2025 | Issue | 01 | | |

^{*} The above mentioned data are typical test values measured on the products; they have to be used as a guide only and can in no event be considered as specifications.



Technical Data Sheet

The information above is provided for our customers only (we accept no liability to any third parties). It reflects our current knowledge and experience of the product and is accurate as of the date of this document. However we do not make any warranty, express or implied or accept any liability in connection with this information or its use. All products are supplied in accordance with our general terms and conditions of sale. This information is for use by technically skilled persons at their own discretion and risk. We accept no liability for the effects of any chemical combinations with any other substance, processes or mixtures of the product which are carried out by our customers or third parties. The users must finally determine suitability of any information or material for any comtempleted use. We reserve our right to make additions, deletions, or modifications to the information at any time without prior notification.

Users of INEOS Inovyn's products should consult the appropriate INEOS Inovyn's Health and Safety literature, or SDS which is available from your sales or technical representative.

In this context, INEOS Inovyn remains available for any further technical information such final article manufacturer may need in that regard.

It is the responsibility of the customer and producer of the end product to ensure that the final material or article complies with all relevant regulations. INEOS Inovyn's products are supplied only on the strict understanding that the customer and the producer of the end product will ensure that the regulations have been complied with. If guidance is required regarding the use of INOVYNTM PVC and BIOVYNTM PVC, please seek assistance from your sales or technical service representative or visit www.inovyn.com.

SUSTAINABILITY

As an industry leader and world-class producer of chlor-alkali and vinyl materials, our products are fundamental to modern society. We embrace the responsibility that accompanies this influential position, and as European market leader, understand our potential to effect **positive change throughout our value chains**.

INEOS Inovyn's strategy towards sustainability is embedded within our **four key pillars** and we aim to position ourselves as an innovation pioneer, developing new solutions at every stage of the journey. Our sustainability pillars are:

Pilar 1 - Responsible production :

Striving for zero incidents and taking an industry-leading approach on the health of our employees, partners involved in the value chain and our impact on the environment.

Pilar 2 - Carbon neutrality :

Accelerating the transition to a Net Zero carbon economy.

Pilar 3 - Circularity :

Advancing circular solutions to maximise efficient use of resources and ensure the long-term value of our products.

Pilar 4 - Value to society :

Products: ensuring that our products continue to bring significant value to society.

People: ensuring that our employees are valued and INEOS Inovyn plays a positive impact on society and the communities in which we operate.

Our ambition is to provide leadership through sustainable innovation.

By harnessing INEOS Inovyn's expertise and technologies, we will meet evolving customer needs and deliver products that are essential to modern life. At INEOS Inovyn, we are members of the leading European Industry associations that align with our portfolio and interests, and that share the same drive towards a sustainable future for our industry.

INOVYN $^{\text{TM}}$, BIOVYN $^{\text{TM}}$, RECOVYN $^{\text{TM}}$ and NEOVYN $^{\text{TM}}$ are trademarks, the property of INOVYN ChlorVinyls Limited. INEOS $^{\text{TM}}$ is a trademark, the property of INEOS Capital Limited.

For the complete trademarks statement, please consult: https://www.inovyn.com/information/trademark-statement/.



| TDS RECOVYN™ PVC 560GA | | | | | |
|------------------------|------------|-------|----|--|--|
| Date | April 2025 | Issue | 01 | | |