

# PVC resins for Thermoplastic Processing



Grades	BIOVYN™ & RECOVYN™ grades	NEOVYN™ grades	K-value ISO 1628-2	Apparent bulk density <sup>1</sup> kg/dm <sup>3</sup> ISO 60	Extrusion									Calendering			Blow moulding	Injection moulding		Characteristics
					Rigid				Plasticised					Rigid	Plasticised		Rigid	Rigid	Plasticised	
					Profiles	Pipes	Sheets	Foam	Profiles	Tube	Cable	Film & sheets	Gaskets	Film	Film & Sheets	Flooring	Bottles			
<b>Homopolymer Suspension resins</b>																				
250SB	x	x	50	0.59				x						x			x	x	High fluidity	
S5736		x	56	0.575	x		x	x						x			x	x	x	
S5737		x	56	0.575	x		x	x						x			x	x	x	
S5745	x		57	0.58	x		x	x						x			x	x	x	
257RF	x		57	0.56	x		x	x						x			x	x	x	
258RD			58	0.54	x		x	x						x			x	x	x	
S6037		x	60	0.56	x		x	x						x				x		
S6045	x		60	0.57	x		x	x						x		x		x		
260RF	x		60	0.54	x		x	x						x				x		
S6261	x		62	0.57	x										x	x				
263RB	x		63	0.56	x	x	x										x			
264GC	x		64	0.53	x	x			x	x	x	x	x		x	x			x	
264PC	x	x	64	0.55	x	x			x	x	x	x	x		x	x			x	
S6545	x		65	0.58	x	x	x													
S6636		x	66	0.575	x	x	x													
S6745	x		67	0.57	x	x	x													
S6770	x		67	0.59	x	x	x													
267RC	x	x	67	0.58	x	x	x													
267RD	x	x	67	0.57	x	x	x													
S7060	x		70	0.49					x	x	x	x	x		x	x			x	
S7060	x		70	0.49						x		x			x				x	Medical applications
271DF			71	0.50					x	x	x	x	x		x	x			x	
271PC	x	x	71	0.50					x	x	x	x	x		x	x			x	
271GA	x	x	71	0.53						x		x			x				x	Medical applications

<sup>1</sup> with antistatic agent addition

Grades	BIOVYN™ & RECOVYN™ Grades	NEOVYN™ grades	K-value ISO 1628-2	Apparent bulk density <sup>1</sup> kg/dm <sup>3</sup> ISO 60	Extrusion									Calendering			Blow moulding	Injection moulding		Characteristics
					Rigid				Plasticised					Rigid	Plasticised		Rigid	Rigid	Plasticised	
					Profiles	Pipes	Sheets	Foam	Profiles	Tube	Cable	Film & sheets	Gaskets	Film	Film & Sheets	Flooring	Bottles			
S7560	x		75	0.49					x	x	x	x	x		x				x	Medical applications. High mechanical properties
S8060	x		80	0.48					x	x	x	x	x		x				x	Medical applications. High mechanical properties
S9060	x		90	0.46					x	x	x	x	x		x				x	Medical applications. Rubber-like properties
<b>Homopolymer Dispersion resins</b>																				
173GB	x		73	-	x														x	For blends with S-PVC resins
<b>Copolymer VC-VAc resins</b>																				
550GA	x	x	50	0.53												x				13% VAc - Vinyl records, inks and glues
557RB	x	x	57	0.55			x							x		x				11% VAc - Improved thermoforming, luxury vinyl tiles, vinyl records

<sup>1</sup> with antistatic agent addition

General purpose grades | Specialty grades | x: BIOVYN™, RECOVYN™ & NEOVYN™ grades