

INOVYN™ PVC resins for Thermoplastic Processing - Main applications

Grades	K-value ISO 1628-2	Apparent bulk density ¹ kg/dm ³ ISO 60	Extrusion									Calendering			Blow moulding	Injection moulding		Characteristics	
			Rigid				Plasticised					Rigid	Plasticised		Rigid	Rigid	Plasticised		
			Profiles	Pipes	Sheets	Foam	Profiles	Tube	Cable	Film & sheets	Gaskets	Film	Film & Sheets	Flooring	Bottles				
Homopolymer Suspension resins																			
250SB	50	0.59				x							x			x	x	High fluidity	
S5736	56	0.575	x		x	x							x			x	x		
S5737	56	0.575	x		x	x							x			x	x		
S5745	57	0.58	x		x	x							x			x	x		
257RD	57	0.61	x		x	x							x			x	x		
257RF	57	0.56	x		x	x							x			x	x		
258RD	58	0.54	x		x	x							x			x	x		
S6037	60	0.56	x		x	x							x			x			
S6045	60	0.57	x		x	x							x		x	x			
260RF	60	0.54	x		x	x							x			x			
S6261	62	0.57	x											x	x				
263RB	63	0.56	x	x	x										x				
264GC	64	0.53	x	x			x	x	x	x	x			x	x			x	
264PC	64	0.55	x	x			x	x	x	x	x			x	x			x	
S6545	65	0.58	x	x	x														
S6636	66	0.575	x	x	x														
S6745	67	0.57	x	x	x														
S6770	67	0.59	x	x	x														
267RC	67	0.58	x	x	x														
267RD	67	0.58	x	x	x														
S7060	70	0.49					x	x	x	x	x			x	x			x	
S7060	70	0.49						x		x				x				x	Medical applications
271DF	71	0.50					x	x	x	x	x			x	x			x	
271PC	71	0.50					x	x	x	x	x			x	x			x	
271GA	71	0.53						x		x				x				x	Medical applications
S7560	75	0.49					x	x	x	x	x			x				x	Medical applications. High mechanical properties
S8060	80	0.48					x	x	x	x	x			x				x	Medical applications. High mechanical properties

¹ with antistatic agent addition

General purpose grades
Specialty grades

Grades	K-value ISO 1628-2	Apparent bulk density ¹ kg/dm ³ ISO 60	Extrusion									Calendering			Blow moulding	Injection moulding		Characteristics
			Rigid				Plasticised					Rigid	Plasticised		Rigid	Rigid	Plasticised	
			Profiles	Pipes	Sheets	Foam	Profiles	Tube	Cable	Film & sheets	Gaskets	Film	Film & Sheets	Flooring	Bottles			
Homopolymer Dispersion resins																		
173GB	73	-	x													x		For blends with S-PVC resins
Copolymer VC-VAc resins																		
550GA	50	0.53												x				13% VAc - Vinyl records, inks and glues
557RB	57	0.55			x							x		x				11% VAc - improved thermoforming

¹ with antistatic agent addition

General purpose grades

Specialty grades

INEOS™ is a trademark, the property of INEOS Capital Limited. INOVYN™ is a trademark, the property of INOVYN ChlorVinyls Limited. You can view our full Trademark Statement on www.inovyn.com/information/trademark-statement/

VI/2019
DISCLAIMER
Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Accordingly, INOVYN ChlorVinyls Limited gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is prevented by law. Freedom under patent, copyright and design cannot be assumed.

